



2086 KEL-AQUA

Interior Acrylic/Urethane Waterborne Gloss Clear

Product Description

Kel-Aqua Interior Acrylic/Urethane Waterborne Gloss Clear is formulated for spray application to interior wood surfaces. This product is fast drying with exceptional clarity. Also available in semi-gloss (2084) and satin (2087) as well as a sanding sealer (2083).

Performance Features

- Excellent Clarity
- Excellent Adhesion
- Easy Application
- Fast Drying
- Water Clean-Up

Product Specifications

Resin Type:	Acrylic/Urethane
Color Range:	Clear
Finish:	80+ @ 60 degrees (MPI GL 6)
Drying Time: (75° F. & 50% R.H.)	To touch: 20 min. To recoat: 30-45 min.
Practical Coverage:	Approx. 300-400 sq ft/gallon
Recommended Dry Film Thickness:	1.0-1.5 mils per coat
Weight Per Gallon:	8.5 lbs.
Solids By Weight:	33%
Solids By Volume:	30%
Shelf Life:	2 years (unopened containers)
Sizes:	One & five gallon containers
V.O.C.	<250 Grams per liter
Clean Up:	Water

Product Analysis (by weight)

PIGMENT COMPOSITION	0.0%
VEHICLE COMPOSITION	100%
Acrylic/Urethane Resin:	32.5%
Water, Surfactants, Defoamers:	67.5%

Surface Preparation

WARNING! If you scrape, sand or remove old paint from any surface, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Carefully clean up with a wet mop or HEPA vacuum. Before you start, find out how to protect yourself and your family by contacting the U.S. EPA/Lead Information Hotline at 1-800-424-LEAD (5323) or log on to www.epa.gov/lead.

General:

All surfaces must be cured, firm, dry and cleaned free of paint, dust, dirt, oil, grease, wax, chalk, mildew or any other contamination or condition that would adversely affect the performance of the coating. Sand glossy, dense or glazed surfaces.

New Wood:

Follow general surface preparation guidelines.. Prior to application of undercoat, sand and putty nail holes and wipe woodwork clean. When staining, check compatibility of stain with Kel-Aqua. Sand after application of Kel-Aqua Sanding Sealer and remove dust with clean damp rag before finish is applied. Do **not** use tack rags.

System Recommendations

Interior Wood:

SEALER: 2083 Kel-Aqua Interior Acrylic Sanding Sealer

FINISH: 2086 Kel-Aqua Gloss Finish.

Application:

Designed for spray application. Do not apply when material, air, and/or surface temperature is below 50°F. Stir thoroughly before and during use. Maintain a wet edge to avoid lap marks.

Thinning

Apply at can consistency. If thinning is necessary to maintain workability, do not exceed one-half pint of water per gallon.

Continued Next Page

2086 KEL-AQUA (cont.)

Precautions

Avoid contact with eyes, skin and clothing. Do not take internally. Wash thoroughly after handling. Close container after each use. Protect from freezing. For additional safety information, consult the Material Safety Data Sheet for this product.

USE ONLY WITH ADEQUATE VENTILATION
KEEP OUT OF REACH OF CHILDREN.

Proper Disposal

For proper disposal of excess material, please contact your local city or county waste management agency.

Limited Warranty: The statements made on this bulletin, product labels or by any of our agents concerning this material are given for information only. They are believed to be true and accurate and are intended to provide a guide to approved construction practices and materials. As workmanship, weather, construction equipment, quality of other materials and other variables affecting results are all beyond our control, Kelly-Moore Paint Company, Inc., does not make nor does it authorize any agent or representative to make any warranty of MERCHANTABILITY OR FITNESS for any purpose or any other warranty, guarantee or representation, expressed or implied, concerning this material except that it conforms to Kelly-Moore's quality control standards. Any liability whatsoever of Kelly-Moore Paint Company, Inc. to the buyer or user of this product is limited to the purchaser's cost of the product itself.