



# 756 QUICK DRY

## Interior Alkyd Eggshell Enamel

THIS PRODUCT MAY NOT BE AVAILABLE IN SOME AREAS DUE TO VOC REGULATIONS  
Contact your Kelly-Moore representative for more information

### Product Description

A professional quality, interior, quick drying, alkyd eggshell enamel. Designed for properly prepared and primed surfaces and features very fast dry allowing rapid recoat times. Cures to a durable, extremely washable, decorative, and protective finish with yellow resistant properties. Good for commercial and residential application.

### Performance Features

- Durable
- Washable
- Quick Drying
- Resists Yellowing
- Multiple Substrate Usage

### Product Specifications

Resin Type:	Alkyd
Color Range:	White and custom tints.
Finish:	Eggshell 10-15 @ 60° (MPI Gloss Level 3)
Drying Time: (75° F. & 50% R.H.)	To touch: 15 minutes To recoat: 1 hour.
Practical Coverage:	Approx. 300-400 sq ft/gallon
Recommended Dry Film Thickness:	1.7-2.2 mils per coat
Weight Per Gallon:	10.5 lbs.
Solids By Weight:	64%
Solids By Volume:	45%
Shelf Life:	2 years (unopened containers)
Sizes:	One & five gallon containers
V.O.C.	<450 Grams per liter
Clean Up:	Mineral Spirits

### Product Analysis (by weight)

PIGMENT COMPOSITION		40%
Titanium Dioxide:		25%
Silicates:		13%
Zinc Oxide:		2%
VEHICLE COMPOSITION		60%
Alkyd Resin:		26%
Solvents, Driers, Additives:		34%

### Surface Preparation

**WARNING!** If you scrape, sand or remove old paint from any surface, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Carefully clean up with a wet mop or HEPA vacuum. Before you start, find out how to protect yourself and your family by contacting the U.S. EPA/Lead Information Hotline at 1-800-424-LEAD (5323) or log on to [www.epa.gov/lead](http://www.epa.gov/lead).

### General:

All surfaces must be cured, firm, dry and cleaned free of dust, dirt, oil, grease, wax, chalky or loose paint, rust, loose mill scale, bond breakers and curing compounds, efflorescence, asphalt stains, mildew or any other contamination or condition that would adversely affect the performance of the coating. Sand glossy, glazed or dense surfaces. Fill holes and surfaces irregularities with a suitable patching compound to match the surface profile.

### System Recommendations

#### Wood, Hardboard:

PRIMER: 985 Flo-Cote Enamel Undercoat

#### Wallboard, Masonry and Plaster:

PRIMER: 971 Acry-Plex PVA Primer/Sealer

#### Metal (Ferrous):

PRIMER: 1710 Kel-Guard Red Oxide Primer

OR: 1711 Kel-Guard White R.I. Primer

#### Metal (Galvanized):

PRIMER: 1722 Kel-Guard Galvanized Iron Primer

FINISH: 756 Quick Dry Eggshell Enamel

### Application

Spray application only. Maintain a wet edge to avoid lap marks. Do not apply when material, air, and/or surface temperature is below 40°F. Extremely high or low temperature may adversely affect dry time. Stir thoroughly before and during use.

*Continued Next Page*

# 756 QUICK DRY (cont.)

## Thinning

This product has been formulated to comply with current regulations. DO NOT THIN.

## Precautions

**Flammable liquid and vapor! Vapor harmful! Vapors may cause flash fire.** Avoid contact with eyes, skin and clothing. Wear a properly fitted respirator. Do not take internally. Wash thoroughly after handling. Close container after each use. For additional safety information, consult the Material Safety Data Sheet for this product.

USE ONLY WITH ADEQUATE VENTILATION.  
KEEP OUT OF REACH OF CHILDREN.

## Proper Disposal

For proper disposal of excess material, please contact your local city or county waste management agency.

**Limited Warranty:** The statements made on this bulletin, product labels or by any of our agents concerning this material are given for information only. They are believed to be true and accurate and are intended to provide a guide to approved construction practices and materials. As workmanship, weather, construction equipment, quality of other materials and other variables affecting results are all beyond our control, Kelly-Moore Paint Company, Inc., does not make nor does it authorize any agent or representative to make any warranty of MERCHANTABILITY OR FITNESS for any purpose or any other warranty, guarantee or representation, expressed or implied, concerning this material except that it conforms to Kelly-Moore's quality control standards. Any liability whatsoever of Kelly-Moore Paint Company, Inc. to the buyer or user of this product is limited to the purchaser's cost of the product itself.